

# Technical Data Sheet

# **KURUMA CLEAR 4:1 K4090**

Rev.1/22

# **Product Description**

KURUMA CLEAR 4:1 K4090 is two-pack acrylic polyurethane topcoat with excellent gloss retention. It is designed for exterior. It has excellent durability, good adhesion, and excellent chemical resistance. It is a high gloss. Can be applied on NC lacquer, acrylic lacquer and 2K urethane paint.

#### **Substrate preparation**

To secure lasting adhesion to the subsequent product all surfaces shall be clean, dry and free from any contamination.

## **Mixing Ratio**

#### - Two Component System

|                               | Weight | Volume |
|-------------------------------|--------|--------|
| KURUMA CLEAR 4:1 K4090 Part A | 100    | 100    |
| KURUMA CLEAR 4:1 K4090 Part B | 25     | 25     |
| Thinner                       | 0-10   | 0-10   |

Mix Part A and Part B, strictly follow mix ratio recommendations before and stir for 2-3 minutes until the mixture is homogeneous before application.

- Pot life 5 hour after mixing Base with hardener @30°C

#### **Thinner**

Kuruma Standard Thinner No.20

#### **Viscosity For Spray**

|               | Viscosity (sec) @30°C |
|---------------|-----------------------|
| Ford Cup No.4 | 13.5 - 15.5           |

Spray gun

Set-up

Na--la ai--

Nozzle size

Spray pressure

**Number of spray coats** 

**Gravity Feed** 

Full pattern Flow - 2.5 turns from fully closed set-up

1.2 - 1.5 mm. (Please refer to spray gun manufacturer)

1.2 - 1.5 Bar

Recommended apply 2 coats

- Light to medium first coat
- Full wet second coat
- Wet film thickness (per coat) 45 to 50 Microns
- Dry film thickness (per coat) 20 to 30 Microns

#### Flash-off time

Between coat: 2 - 3 mins

### **Drying time**

**Shelf life** 

| Drying time    | Air dry ( 30 °C) |
|----------------|------------------|
| Surface dry    | 20 - 30 mins     |
| Polishing time | 6 - 8 hrs        |
| Full cure      | 7 days           |

#### **Handling and Storage**

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition.

- 48 months at <40 °C
  - The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

#### **Safety and Disposal**

- Please observe the precautionary notices displayed on the container. Use under well ventilated conditions.
  Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.
- For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Safety Data Sheet.